

POROVNÁVACÍ TABULKA NOREM W.Nr. - EN - DIN - AISI - ČSN

W.Nr.	EN	DIN	AISI	ČSN
1.0035	S185	St 33	---	10 004
1.0037	S235JR	St 37-2	---	---
1.0038	S235JRG2	RSt 37-2	---	11 375
1.0044	S275JR	St 44-2	---	---
1.0050	E295	St 50-2	---	11 500
1.0570	S355J2G3	St 52-3	---	11 523
1.0060	E335	St 60-2	---	11 600
1.0070	E360	St 70-2	---	11 700
1.0116	S235J2G3	St 37-3 N	---	11 378
1.0128	S275JRC	St 44-2	---	---
1.0138	S275J2H	RoSt 44-3	---	---
1.0143	S275JO	St 44-3 U	---	11 443
1.0144	S275J2G3	St 44-3 N	---	11 448
1.0149	S275JOH	RoSt 44-2	---	---
1.0254	SPT360	St 37-0	---	11 353
1.0305	P235GH	St 35-8	---	12 021
1.0330	DC01	St 2, St 12	---	11 321
1.0335	DD13	StW 24	---	11 330
1.0338	DC04	St 4, St 14	---	11 325
1.0345	P235GH	H I	---	11 368
1.0347	DC03	RRSt 3, RRSt 13	---	---
1.0405	---	St 45-8	---	12 022
1.0406	C25	C 25	---	12 030
1.0421	SPT510	St 52.0	---	11 523
1.0425	P265GH	H II	---	11 416
1.0429	L290MB	StE 290.7 TM	---	---
1.0438	B500N	BSt 500 S	---	---
1.0457	L240NB	StE 240.7	---	---
1.0473	P355GH	19 Mn 6	---	---
1.0481	P295GH	7Mn4	---	13 030
1.0484	P290NB	StE 290.7	---	---
1.0487	P275NH	WStE 285	---	---
1.0488	P275NL1	TStE 285	---	---
1.0490	S275N	StE 285	---	---
1.0491	S275NL	TStE 285	---	---
1.0493	S275NH	StE 285	---	---
1.0501	C35	C 35	1035	12 040
1.0503	C45	C 45	1045	12 050
1.0511	C40	C 40	---	12 041
1.0535	C55	C 55	---	12 060
1.0539	S355NH	StE 355	---	---
1.0540	C50	C 50	1050	12 051
1.0546	S355NL	TStE 355	---	---
1.0549	S355NLH	TStE 355	---	---
1.0553	S355JO	St 52-3 U	---	---
1.0554	S355JOC	St 52-3 U	---	---
1.0562	P355N	StE 355	---	---

1.0565	P355NH	WStE 355	---	---
1.0566	P355NL1	TStE 355	---	11 503
1.0569	S235J2G3C	St 52-3 N	---	---
1.0570	S355J2G3	St 52-3 N	---	11 523
1.0576	S355J2H	RoSt 52-3	---	---
1.0578	L360MB	StE 360.7 TM	---	---
1.0582	L360NB	StE 360.7	---	13 126
1.0601	C60	C 60	---	12 061
1.0976	S355MC	QStE 360 TM	---	---
1.0977	S355NC	QStE 360 N	---	---
1.0980	S420MC	QStE 420 TM	---	---
1.0981	S420NC	QStE 420 N	---	---
1.0982	S460MC	QStE 460 TM	---	---
1.0984	S500MC	QStE 500 TM	---	---
1.0986	S550MC	QStE 550 TM	---	---
1.1104	P275NL2	EStE 285	---	---
1.1106	P355NL2	EStE 355	---	---
1.1170	28Mn6	28 Mn 6	---	13 141
1.1191	C45E	Ck 45	1045	---
1.1201	C45R	Cm 45	---	---
1.3505	100Cr6	100 Cr 6	52100	14 109
1.3536	100CrMo7-3	100 CrMo 63	---	---
1.4006	X12Cr 13	X12Cr 13	410	17021
1.4021	X20Cr13	X 20 Cr 13	420	17 022
1.4057	X19CrNi17-2	X20 CrNi 17 2	431	---
1.4104	X14CrMoS17	X12CrMoS17	430F	---
1.4122	X39CrMo17-1	X 35 CrMo 17	---	---
1.4301	X5CrNi18-10	X 5 CrNi 18 10	304	17 240
1.4305	X8CrNiS18-9	X 10 CrNiS 18 9	303	---
1.4306	X2CrNi 19-11	X2CrNi 19 11	304L	17249
1.4313	X3CrNiMo 13-4	X3CrNiMo 13 4	SA 41500	---
1.4404	X2CrNiMoN17-12-2	X 2 CrNiMo 17 122	316L	17 349
1.4439	X3CrNiMoN17-13-5	X 3 CrNiMoN 17 13 5	---	17 350
1.4460	X3CrNiMoN27-5-2	X 4 CrNiMo 27 5	---	---
1.4462	X2CrNiMoN22-5-3	X 2 CrNiMoN 22 5	---	---
1.4539	X1NiCrMoCuN25-20-5	X 2 NiCrMoCu 25 20 5	---	---
1.4541	X6CrNiTi18-10	X 6 CrNiTi 18 10	321	17 248
1.4571	X6CrNiMoTi17-12-2	X 6 CrNiMoTi 17 12 2	316Ti	17 348
1.4713	X10CrAl7	X 10 CrAl 7	---	17 113
1.4828	X15CrNiSi20-12	X 15 CrNiSi 20 12	309	17 251
1.4841	X15CrNiSi25-20	X 15 CrNiSi 25 20	314	17 255
1.5415	16Mo3	15 Mo 3	ASTMA204GrA	15 020
1.5622	14Ni6	14Ni6	ASTMA350LF5	---
1.5752	14NiCr14	14 NiCr 14	3415, 3310	16 420
1.5919	15CrNi6	15 CrNi 5	---	16 220
1.6582	34CrNiMo6	34 CrNiMo 6	---	16 343
1.6903	X10CrNiTi18-10	X 10 CrNiTi 18 10	---	17 246
1.7035	41Cr4	41 Cr 4	---	14 140
1.7131	16MnCr5	16MnCr 5	5115	14 220

1.7147	20MnCr5	20MnCr 5	---	14 221
1.7218	25CrMo4	25CrMo 4	4130	15 130
1.7220	34CrMo4	34CrMo 4	4137, 4135	15 131
1.7225	42CrMo4	42CrMo 4	4140	15 142
1.7335	13CrMo4-5	13CrMo 4 4	ASTMA182	15 121
1.7380	10CrMo9-10	10CrMo 9 10	ASTMA182F.22	15 313
1.7707	30CrMoV9	30 CrMoV 9	---	15 241
1.7733	24CrMoV5-5	24 CrMoV 5 5	---	15 320
1.7735	14CrMoV6-9	14 CrMoV 6 9	---	---
1.8159	51CrV4	50 CrV 4	6150	15 260
1.8521	15CrMoV5-9	15 CrMoV 5 9	---	---
1.8550	34CrAlNi7	34 CrAlNi 7	---	---
1.8903	S460NL	TStE 460	---	---
1.8912	S420NL	TStE 420	---	---
1.8928	S690QL	TStE 690 V	---	---
1.8935	P460NH	WStE 460	---	---
1.8953	S460NH	StE 460	---	---
1.8963	S355J2G1W	WTSt 52-3	---	15 127

